

Via Caduti della Liberazione, 57 21040 Uboldo (VA) – Italia Tel: +39 02 964121 Fax: +39 02 96412294

Web: www.eurocel.it

PRODUCT INFORMATION **EUROCEL MSK 6265**

DESCRIPTION

Masking tape for car repair.

PRODUCT DATA

| Backing | 58 g/m² saturated crepe paper; blue | |
|----------|---|--|
| Adhesive | Natural rubber and resins solvent based | |

| | Unit | Value | Method |
|---------------------|--------|---------------|----------|
| Total thickness | mm | 0.125 | PSTC 133 |
| Adhesion to steel | N/25mm | 4.3 | PSTC 101 |
| Tensile strength MD | N/25mm | 85 | PSTC 131 |
| Elongation at break | % | 8 | PSTC 131 |
| Temp. Resistance | °C | 80°C (30 min) | = |

APPLICATION

Masking tape suitable for car repair applications when temperature does not exceed 80°C.

| Features | Benefits | | | |
|--|--|--|--|--|
| Natural rubber and resins solvent based adhesive | ✓ Good adhesion even on irregular surfaces ✓ Easy removal without adhesive residue, if removed as soon as paint is dry ✓ Heat resistant up to 80°C (30 min) | | | |
| Saturated paper backing | ✓ Well conformable to most shaped surfaces ✓ Hand tearable ✓ Compatible with most common paints and lacquers ✓ Removable without breaking | | | |

CONDITIONS OF USE AND CONFORMITY

Product shelf life and storage: 12 months; suggested storage temperature shall range from 15°C to 25°C with max. relative humidity of 65%. Material shall be stored away from heat sources and possibly kept in original package, avoiding light exposure as well. When temperatures are lower than suggested, it is always required to recondition the tape at normal temperature before use. This information is given to the best of Sicad's knowledge. Values are typical and do not constitute a specification. Customers are required to do their own testing under their working condition for their intended application. Any liability arising in respect of our products will be limited to the value of those products charged to the customer excluding any consequential loss.