



Sicad s.p.A.

Via Caduti della Liberazione, 57
21040 Uboldo (VA) – Italia
Tel: +39 02 964121 Fax: +39 02 96412294
Web: www.eurocel.it

PRODUCT INFORMATION

EUROCEL MASKOPRI

DESCRIPTION

Masking system for protection during painting jobs where wide areas should be covered.

PRODUCT DATA

Backing	Paper masking tape coupled with 10 my HDPE; transparent film
Adhesive	Natural rubber and resins solvent based

	Unit	Value	Method
Total thickness	mm	0.125 (tape)*	PSTC 133
Adhesion to steel	N/25mm	4.3 (tape)	PSTC 101
Tensile strength MD	N/25mm	85 (tape)	PSTC 131
Elongation at break	%	7.5 (tape)	PSTC 131
Temp. Resistance	°C	80°C (30 min)	=

APPLICATION

Easy and ready to use masking system, obtained by bonding a paper masking tape and a clear HDPE film. Very easy to use, it works on different surfaces. Always well positioned thanks to its electrostatic properties, the HDPE film is treated so as to accept paints and varnishes, thus preventing dripping. Suitable for covering walls, furniture, doors, frames, etc in professional jobs, DIY and industrial painting. Available in several HDPE film width.

*Higher width rolls have thicker tape

Features	Benefits	
Natural rubber and resins solvent based adhesive	<ul style="list-style-type: none"> ✓ Good adhesion even on irregular surfaces ✓ Heat resistant up to 80°C (30 min) 	<ul style="list-style-type: none"> ✓ Easy removal without adhesive residue, if removed as soon as paint is dry
Saturated paper backing (masking tape)	<ul style="list-style-type: none"> ✓ Well conformable to most shaped surfaces ✓ Removable without tearing 	<ul style="list-style-type: none"> ✓ Compatible with most common paints and lacquers
HDPE transparent film	<ul style="list-style-type: none"> ✓ Resistant ✓ Electrostatic 	<ul style="list-style-type: none"> ✓ Treated to accept paints and varnishes

CONDITIONS OF USE AND CONFORMITY

Product shelf life and storage: 12 months; suggested storage temperature shall range from 15°C to 25°C with max. relative humidity of 65%. Material shall be stored away from heat sources and possibly kept in original package, avoiding light exposure as well. When temperatures are lower than suggested, it is always required to recondition the tape at normal temperature before use. This information is given to the best of Sicad's knowledge. Values are typical and do not constitute a specification. Customers are required to do their own testing under their working condition for their intended application. Any liability arising in respect of our products will be limited to the value of those products charged to the customer excluding any consequential loss.

MK015EN_REV02_MASKOPRI

Società Italiana Cellophane Adesivo
P.I. e C.F. IT 00220060123
Iscrizione R.E.A. Varese n. 129175
Reg. Imprese Varese n. 00220060123
Capitale Sociale € 15.000.000 i.v.